



Prepared For:
Dan Resnic
Strata Various Product Design
311 N. Robertson Blvd. #318
Beverly Hills, CA 90211

Submitted By:
Nelson Laboratories, Inc.
6280 S. Redwood Rd.
Salt Lake City, UT 84123-6600
801-290-7500
Page 1 of 3

DIMENSIONS AND TENSILE PROPERTIES OF RUBBER CONDOMS - FINAL REPORT

Laboratory Number:	390327
Procedure Number:	STP0068 REV 03
Standard Method:	ASTM D3492
Sample Source:	Strata Various Product Design
Sample Identification:	ORIGAMI SILICONE CONDOM - SVPD Lot #94 P.O. #SVPD-080207-002
Deviations:	None
Statement of Uncertainty:	Available upon request
Sample Received Date:	17 Aug 2007
Lab Phase Start Date:	11 Sep 2007
Lab Phase Completion Date:	16 Oct 2007
Report Issue Date:	17 Oct 2007

RESULTS:

The results are reported in Tables 1-2.


Jennifer Gygi, B.S. SM(NRM)
Study Director


Study Completion Date

JAG/ad



All reports and letters issued by Nelson Laboratories, Inc. are for the exclusive use of the sponsor to whom they are addressed. These results relate only to the samples tested. Reports may not be reproduced except in their entirety. No quotations from reports or use of the corporate name is permitted except as expressly authorized by Nelson Laboratories, Inc. in writing. The significance of any data is subject to the adequacy and representative character of the samples rendered for testing. Nelson Laboratories, Inc. warrants that all tests are performed in accordance with established laboratory procedures and standards. Nelson Laboratories, Inc. makes no other warranties of any kind, express or implied. Nelson Laboratories, Inc. expressly states that it makes no representation or warranty regarding the adequacy of the samples rendered for testing for any specific use or application, that determination being the sole responsibility of the sponsor. Nelson Laboratories' liability for any loss or damage resulting from its actions or failure to act shall not exceed the cost of tests performed and it shall not be liable for any incidental or consequential damages.



Strata Various Product Design
Lab Number 390327

Dimensions and Tensile Properties
of Rubber Condoms
Page 2 of 3

TABLE 1. Results
ORIGAMI SILICONE CONDOM - SVPD

SAMPLE IDENTIFICATION	LENGTH (mm)	WIDTH (mm)	MEDIAN THICKNESS (mm)
1	175	52	0.62
2	175	52	0.60
3	175	52	0.52
4	175	52	0.60
5	175	52	0.57
6	175	52	0.56
7	175	52	0.63
8	175	52	0.62
9	175	52	0.63
10	175	52	0.57
11	175	52	0.62
12	175	52	0.55
13	175	52	0.59

NELSON
LABORATORIES

Strata Various Product Design
Lab Number 390327

Dimensions and Tensile Properties
of Rubber Condoms
Page 3 of 3

TABLE 2. Results
Trojan Latex Condom

SAMPLE IDENTIFICATION	LENGTH (mm)	WIDTH (mm)	MEDIAN THICKNESS (mm)
1	185	52	0.11